



AC A535-AT

Dual-curable, Polishable, Medium Viscosity Epoxy Adhesive

Features

- Medium viscosity
- High Tg
- Low shrinkage
- High temperature resistance

Description

- Dual-curable epoxy adhesive

APPLICATIONS

AC A535-AT is suitable for bonding glass to glass, glass to ceramic, ceramic to ceramic, ceramic to metal or plastic parts to ceramic or metal parts, etc. It is recommended to be used where instant fix for the aligned parts can be accomplished by UV, then thermal post cure of the fixed parts provides complete cure in areas where UV light cannot penetrate.

TYPICAL PROPERTIES

Liquid

Viscosity (cps, 25 °C)	1000 – 1,300
Storage (°C)	15 - 25
Shelf life (15 - 25 °C)	6 months
Pot life (15 - 25 °C)	3 months

Cured film

Shrinkage (linear, %)	< 0.5
Outgas, weight % (per Telcordia GR-1221)	0.01
Outgas, weight % (per MIL-STD 883/5011)	0.05
Hardness – Shore D	90
Glass transition temperature of fully cured adhesive (DMA, °C)	160
Refractive index of cured film (25°C)	
@ 589 nm	1.572
@ 1310 nm	1.556
@ 1550 nm	1.553
Coefficient of thermal expansion (TMA), 75 µm film	
below Tg (x10 ⁻⁶), °C ⁻¹	42
above Tg (x10 ⁻⁶), °C ⁻¹	86
Physical properties tested at 25°C, 50% RH (ASTM D638)	
Elongation (%)	4
Modulus, psi (kgf/mm ²)	245,000 (172)

UV curing conditions

Flood curing system – UV dose (J/cm²), air 3.5 – 4.0

UV curing conditions

Spot cure system – UV dose (J/cm²), air

250 – 450 nm filter	30 – 50
320 – 500 nm filter	35 – 50

Heat curing conditions:

@ 125 °C (if use heat only)	4-5 hrs
(if use UV and heat)	3-4 hrs
@ 150 °C (if use heat only)	2-3 hrs
(if use UV and heat)	1-2 hr
@ 180 °C (if use heat only)	1hr
(if use UV and heat)	0.5-1 hr

***Minimum intensity recommended for Spot lamp system: 300 mW/cm²

***Minimum intensity recommended for Flood lamp system: 125 WPI or 49 W/cm

***If a low intensity Spot lamp is used, intensity of 70 – 100 mW/ cm², we recommend a cure time of 7 to 10 minutes

SAFETY AND HANDLING

The un-cured adhesive can be cleaned from apparatus with isopropyl alcohol (IPA), methyl ethyl ketone (MEK), or commercial alcohol based cleaning solution.

Use caution in handling this material. Avoid direct skin and eye contact. Use only in well ventilated areas. Use protective clothing, **gloves and safety goggles**. Read [Material Safety Data Sheet](#) before handling.

The information presented here represents our best available information and is believed to be reliable, but it does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to insure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product.