



# FS-2600

## Optically Clear Working Stamp Resins for Photo NIL Applications

### ADVANTAGES FEATURES:

- Fluorine free, UV-curable working stamp resin
- Low viscosity for easy spin process
- **Excellent Chemical Resistance** (high resistance to etching from imprint resins): minimal height gain for multiple imprints
- Excellent mechanical and thermal stability
- **NO ANTI-STICK Layer is needed**
- Optically clear
- Solvent Free – ready to use
- Long shelf life at room temperature

**APPLICATIONS:** Working Stamp fabrication

**PRODUCT DESCRIPTION:** UV-curable acrylate material for radical polymerization

#### GENERAL USAGE INFORMATION:


**Storage:** room temperature storage (15-30°C) in the original container is required.

#### SAFETY AND HANDLING

The uncured resin can be cleaned with isopropyl alcohol (IPA), methyl ethyl ketone (MEK), acetone, or xylene. Avoid direct skin and eye contact. Use only in well ventilated areas. Use protective clothing, **gloves and safety goggles**. Read [Safety Data Sheet](#) before handling.

TDS updated: V1-112023

### WORKING STAMP PROCESS FLOW:



### APPLICATION NOTES:

#### Master Stamp or Master Mold preparation:

To protect the master Stamp/Mold surface the use of a release agent or antistick agent is recommended. The common anti-stick or release agents are trichloro(1H,1H,2H,2H-perfluorooctyl)silane (CAS # 78560-45-9) or trimethoxy(1H,1H,2H,2H-perfluorooctyl)silane (CAS# 85857-16-5).

#### Substrate conditions:

To obtain the optimal performance for FS-2600, plastic or glass substrates should be primed or should have an adhesion promotor layer.

**Dispense process:** droplet dispense method for capillary flow, or casting method, or spin coating method are suitable for film forming

Suggested spin conditions for spin coating method for 10 micron layer thickness:

Speed: 2,000 to 3,000 rpm

Time: 25 to 35 seconds

Acceleration: 800 to 1,000 rpm/sec

A droplet dispense / Casting method can avoid excess use of working stamp resin

**Layer thickness:** 5 to 200 micron

**UV CURING CONDITIONS:** UV dose (J/cm<sup>2</sup>) = 10 to 20

\*Metal halide / Mercury UV: UV-A (320-400 nm), intensity: 50-1,000 mW/cm<sup>2</sup>

Suggested curing conditions: 200 mW/ cm<sup>2</sup> x 50 sec

Atmosphere: cure between two substrates or in an inert atmosphere (oxygen-free)

\*or LED-365 nm, UV light intensity: 100 to 1,000 mW/ cm<sup>2</sup>

Suggested curing conditions: 200 mW/ cm<sup>2</sup> x 100 sec

Atmosphere: cure between two substrates or in an inert atmosphere (oxygen-free)

The information presented here represents our best available information and is believed to be reliable, but it and does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to ensure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product.

Addison Clear Wave Coatings, Inc., 3555 Legacy Blvd, St. Charles, IL 60174 USA

Tel: +1 630-444-1658, [addisoncw.com](http://addisoncw.com)




## FS-2600 (continue)

**Processing environment:** process at temperature between 20 – 30 °C at relative humidity of 40-70% and process under yellow light.

### TYPICAL PROPERTIES:

Before cure (liquid)	FS-2600
Viscosity (cps, 25 °C)	200 - 300
Density (g/mL)	1.1
Shelf life (15 - 25 °C)	6 months
Working life (20 - 30 °C)	3 months
After curing - cured film	FS-2600
Volume shrinkage (%)	3-5
Tg (DMA, °C)	147
Young's Modulus (Gpa)	1
Elongation (%)	5
Contact angle of water in air (°)	117
% Transmission (400 to 900 nm)	>90
Refractive index @ 589 nm	1.505



The information presented here represents our best available information and is believed to be reliable, but it and does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to ensure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product.

Addison Clear Wave Coatings, Inc., 3555 Legacy Blvd, St. Charles, IL 60174 USA

Tel: +1 630-444-1658, [addisoncw.com](http://addisoncw.com)